

MPLA L606F-1011

APPLICATIONS（产品说明）

ZHOSO® L606F-1011 是一款基于聚乳酸PLA/PBAT 改性的吹膜产品，PLA/PBAT跟无机物粉体复合，提升产品成膜性，具有高强度，良好的透明度，低温热封性。

Properties（物理性能）

Mechanical 项目	Test Condition 条件	S. I. Unit 单位	Test Standard 测试方法	S. I. Typical Value 额定值
Density 比重		g/cm³	ASTMD792	1.3
Flow index 熔体流动速率	190° C/2.16 kg	g/10 min	ASTMD1238	3.5
Tensile Strength 拉伸强度	50mm/min	Mpa	ASTMD638	18
Tensile Strain at Break 断裂伸长率	50mm/min	%	ASTMD638	30.2
Flexural Strength 弯曲强度	10mm/min	Mpa	ASTMD790	52.2
Flexural Modulus 弯曲模量	10mm/min	Mpa	ASTMD790	2450
Izod Notched Impact Strength 缺口冲击强度	23° C	KJ/m²	ASTMD256	5.8
melting point 熔点		° C	ASTMD4591	150

Application guide（应用指南）

- 1) 烤料时间：2-3小时 烤料温度：60° 左右。
- 2) 吹膜温度：130° -150°
- 3) 热封温度：平口机180° - 200° R机 280° -350°

remarks（备注）：

1. The above data are laboratory test data, which is only a reference when applicable to customers, and is not used as a guarantee of quality indicators and for any other purposes
以上数据为实验室测试数据，只供客户参考，不作为品质指标的保证及其他任何用途的保证
2. The above application guide parameters are for reference only, and the above processes can be adjusted appropriately according to different models, molds and product requirements
上应用指南参数仅供参考，可以根据不同机型/模具以及产品要求，对上述工艺进行适当调整



关注微信公众号

广东众塑降解材料有限公司

东莞市桥头镇华夏一路30号

400-031-2662